

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 238 904 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**11.09.2002 Bulletin 2002/37**

(51) Int Cl.7: **B63B 9/00, C09D 167/06,  
C09D 163/10**

(21) Application number: **02001568.1**

(22) Date of filing: **23.01.2002**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

- **Whitley, Kimberly Ann**  
Hamilton, Ohio 45011 (US)
- **Schaefer, Louis Paul**  
Cincinnati, Ohio 45212 (US)

(30) Priority: **05.03.2001 US 799211**


(71) Applicant: **ILLINOIS TOOL WORKS INC.**  
**Glenview, Cook County, Illinois 60025 (US)**

(74) Representative: **Vetter, Ewald Otto et al**  
**Meissner, Bolte & Partner**  
**Anwaltssozietät GbR**  
**Postfach 10 26 05**  
**86016 Augsburg (DE)**

(72) Inventors:  
• **Anderson, Robert Phillip**  
**Westchester, Ohio 45069 (US)**

(54) **Wood replacement system and method**

(57) Methods, compositions and boat hulls are disclosed using and forming a wood replacement surface. The wood replacement surface is used as a replacement or substitute for wood surfaces. The wood replacement surface of the present invention has improved characteristics, such as strength and water resistance, compared to conventional wood surfaces. The wood replacement surface is resistant to environmental conditions such as water, heat and sunlight. The wood replacement surface is easier to apply than conventional wood surfaces.



**FIG. 1**

**Description**

## FIELD OF THE INVENTION

5 **[0001]** This invention relates to environmentally resistant fabrication materials, and more particularly, to a barrier coat layer and core material to be used in combination with other manufactured materials to provide an environmentally resistant structure which can be used in place of wood surfaces.

## BACKGROUND OF THE INVENTION

10 **[0002]** Wood has long been used as a material for structures used in intense environmental conditions. Wood is used for structures such as decks, boat hulls, docks and the like. These structures face a wide variety of environmental conditions such as water, heat, sun and humidity. These conditions can cause the wood to suffer damage such as blistering, weakening, warping, deforming and rotting. This damage is highly undesirable and can cause disastrous results in structures such as boat hulls.

15 **[0003]** Various methods have been used to prevent damage to wood subjected to environmental conditions. These methods usually employ stains, marine varnishes and other protective coatings that are physically applied to the wood surface to attempt to protect the wood. These methods require repeated maintenance and monitoring and even then often fail. Additionally, they require a large amount of costly manual labor.

20 **[0004]** Some methods and systems have avoided the problems of wood being exposed to environmental conditions by building structures, such as boat hulls, out of other materials, such as fiberglass or aluminum, instead of wood. One such method is U.S. Patent No. 5,601,049, Hordis et al, where a boat hull is protected against blistering on the under-water surface by using successive layers of fiber reinforced synthetic plastic and having an outer gelcoat layer and a barrier coat material of microspheres thoroughly mixed in a synthetic resin. Another method and system is disclosed by U.S. Patent No. 5,277,145, Hordis, which teaches inserting a core of syntactic foam between an inner transom wall and an outer transom wall.

25 **[0005]** Another method of avoiding problems of wood being exposed to environmental conditions is seen in fabricating high strength boat transoms. Many transoms are fabricated using marine or exterior grade plywood with layers of fiberglass and resin on each face. However, after a short time, small leaks develop in the plastic skin and fastener holes. This causes water to be soaked up by the plywood core which in turn causes the plywood to suffer damage. U. S. Patent No. 5,036,788, Unger, describes a method of doing so and attempts to avoid leaks by applying an outer skin to the wood while the transom is still in the hull mold. However, Unger requires the use of molds and forms which can make it difficult in application.

30 **[0006]** Another method and system is disclosed by U.S. Patent 5,207,172, Wolter, which discloses forming a boat deck surface comprising at least two layers. One layer contains a slow hardening elastic resin and a solid particulate and another layer contains a slow hardening elastic resin, a solid particulate and a coloring agent. Wolter is generally used for repairing boat decks. Wolter uses a flowable epoxy and requires forming a first layer, curing, then forming a second layer and curing.

35 **[0007]** Other methods attempt to reinforce plywood or wood. However, the inherent weakness of wood in resisting flexibility and resisting environmental exposure remains causing the results of these methods to be less than desirable.

40 **[0008]** What is needed is a method and system for replacing wood surfaces with a non-wood surface that is highly resistant to environmental conditions and easy to fabricate and apply.

## SUMMARY OF THE INVENTION

45 **[0009]** This need is met by the present invention by providing an easily applied coating or surface that is highly resistant to environmental conditions.

**[0010]** A method of replacing a wood surface with a wood replacement surface according to one embodiment of the present invention is disclosed. A wood surface is removed from a structure. A wood replacement composition is sprayed or poured on the surface of the structure. The wood replacement composition is catalyzed forming the wood replacement surface. The wood replacement surface is resistant to environmental conditions.

50 **[0011]** Also disclosed is a composition and a method of fabricating a sprayable, pourable composition which can be used to produce articles and surfaces where wood or particle board might otherwise be used. One or more resins are provided. A monomer is provided. A thickening agent such as clay is provided. The provided materials are mixed. Fumed silica (optional) and one or more accelerators are provided. The provided materials are mixed. Hollow spheres and other fillers are then provided. The provided materials are mixed forming the composition.

55 **[0012]** A boat hull according to another embodiment of the present invention is disclosed. The boat hull includes at least one laminated fiber layer and a wood replacement layer. The at least one laminated fiber layer has an outer

surface, which includes a gel coat. The wood replacement layer is formed from mixing resin, a monomer, thickening agent, accelerators, hollow spheres and other fillers. The wood replacement layer is formed interiorly of the gel coat layer.

## BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

**[0013]** The following detailed description of the present invention can be best understood when read in conjunction with the accompanying drawings, where like structure is indicated with like reference numerals.

**[0014]** Figure 1 illustrates a method of fabricating a sprayable, pourable composition according to one embodiment of the present invention.

**[0015]** Figure 2 illustrates a method of replacing a wood surface with a wood replacement surface according to another embodiment of the invention.

**[0016]** Figure 3 is a cross-section of a boat hull according to another embodiment of the present invention.

**[0017]** Figure 4 is a cross-section of a boat hull according to another embodiment of the present invention.

## DETAILED DESCRIPTION OF THE INVENTION

**[0018]** Figure 1 illustrates a method of fabricating a sprayable, pourable composition which can be used to produce articles and surfaces where wood or particle board might otherwise be used. One or more resins are provided at block 101. Typically, a polyester resin of 40-60 percent, by weight, of the composition and a vinyl ester resin of 10-20 percent are provided. Suitable resins can be obtained from Reichhold Chemical. A monomer may be added in an amount of 0-20%.

**[0019]** The monomer is provided at block 102. The monomer, which may be a styrene monomer, typically is 5-20 percent of the composition. By using lower amounts of the styrenic component, a low VOC composition is produced. It is also possible to use non-styrenic, VOC compliant materials in place of the styrene monomer. A thickening agent, such as thixotropic clays, provided at block 103. Suitable thixotropic clays can be purchased from Southern Clay Products, Inc. They may be present in an amount of 1-15%. The provided materials are mixed together for about 15 minutes at block 104. They can be mixed in a conventional mixer.

**[0020]** Fumed silica is provided at block 105. The preferred amount fumed silicon is 0-3%. It may be added before or after block 104. Fumed silicas can be obtained from Dè Gussa Co. among others. One or more accelerators are provided at block 106. The one or more accelerators can be DMPT, DMA, DMAA, cobalt octoate, potassium octoate, copper naphthanate and quaternary ammonium salts. The accelerators generally comprise 0.1-5 percent of the composition. The provided materials are mixed together for about 5 minutes at block 107.

**[0021]** Fillers, i.e. hollow spheres or microspheres and optionally other fillers, are provided at block 108. Hollow microspheres can be obtained from PQ Corporation, Expencel Inc., and others. Other fillers include wallastonite fibers (available from Nyco Minerals, Inc.) and mica fillers (available from Zenca Industrial Minerals). The fillers generally comprise 1-25 percent of the total composition. The provided materials are mixed together for about 20 minutes at block 109 forming the sprayable, pourable composition. The composition is filtered through a mesh filter at block 110.

**[0022]** This composition can then be poured or sprayed along with a catalyst to form an article or surface which is environmentally resistant. It is useful in producing boat hulls, docks, decks, floors, buildings and other structures which are used in harsh environmental conditions.

**[0023]** Figure 2 illustrates a method of replacing a wood surface with a wood replacement surface according to another embodiment of the present invention. A wood surface is removed from a structure at block 201. The wood surface may be comprised of a material such as plywood or any other wood material or product commonly used. The structure can be a boat hull, a dock, a deck floor, building or other structure. Generally, the present invention can be used as a replacement for wood anywhere the wood surface and structure are subjected to intense environmental conditions such as water, humidity and sunlight. The damaged wood surface can be removed by any number of conventional methods such as sanding, sawing or cutting.

**[0024]** A wood replacement composition, which is the same as the composition discussed above, is sprayed or poured on the surface of the structure in areas where the wood surface was previously removed at block 202. The composition is added to a catalyst and applied. When sprayed, it can be mixed with a catalyst either externally or internally of the spray nozzle as disclosed in U.S. Patent No. 5,371,117, which is incorporated herein by reference. A suitable catalyst is methyl ethyl ketone peroxide, however other materials may be used as a catalyst. The wood replacement surface formed is resistant to environmental conditions such as water, humidity and sunlight. The wood replacement surface forms a barrier against water vapor transmission and is highly resistant to rot. Additionally, the wood replacement surface has good compressive, shear, flexural, and tensile strength, has good memory and is able to hold a fastener.

**[0025]** In alternate embodiments, the wood replacement surface can be formed on the surface of structures without

removing a wood surface. The wood replacement surface can be formed on top of an existing wood surface or can be formed on the surface of the structure instead of forming a wood surface.

[0026] Figure 3 illustrates a boat hull according to another embodiment of the present invention. The boat hull comprises at least one fiber reinforced synthetic plastic layer 301 and a wood replacement layer 302. The boat hull also has an outer surface 303. Laminated fiber layers are commonly used in boat hull construction, see Hordis U.S. Patent No. 5,601,049, which is hereby incorporated by reference.

[0027] The wood replacement layer 302 is formed between the outer surface 303 and inner surface of at least one layer 301. The outer surface 303 may for example be gel coat 304, barrier layer 305 and skin coat 306 of the type described in Hordis U.S. Patent No. 5,601,049. The wood replacement layer is formed with a desired thickness by mixing the wood replacement composition, i.e. resin, a monomer, accelerators, thickening agent and fillers with a catalyst and applying it by spraying or pouring.

[0028] Figure 4 is similar to figure 3 except that the wood replacement layer 302 of the present invention is used in place of barrier layer 305 of figure 3 and the core 307 may be another wood replacement layer like 302, a standard core material as shown in Hordis U.S. Patent No. 5,601,049, or a foam core as in Hordis U.S. Patent No. 5,277,146.

[0029] The desired thickness of the wood replacement layer 302 can vary between 1 and 750 mils. However, an example of a desired thickness is 3/8 of an inch. With such a thickness, the wood replacement layer would have a shear strength of about 705 psi, a compressive strength of about 2544 psi and a water absorption of about 0.2 percent.

[0030] Table 1 shows experimental results of a 3/8 inch thick wood replacement layer formed according to an embodiment of the present invention compared with 3/8 inch thick plywood and 3/8 inch balsa. It can be readily seen that the wood replacement layer provides shear strength and compressive strength. Furthermore, the wood replacement layer is superior at preventing water absorption.

TABLE 1

	3/8 Balsa	3/8 Plywood	wood rep. sur.
Shear Strength (psi)	358	263	705
Shear Modulus (psi)	5347	6210	6538
Flex Strength (psi)	11025	7917	19427
Flex Modulus (msi)	1.03	0.97	0.88
Tensile Strength (psi)	10,091	9,019	7,191
Tensile Modules (msi)	.8	1.23	.55
Compressive Str. (psi)	604	901	2544
Compressive Mod. (psi)	4739	8917	49645
Fastener Withdrawal (lbs)	290	294	371
Water Absorption (%)	4.7	15.3	0.2

[0031] The wood replacement surface of the present invention is easier to apply than conventional wood surfaces. The surface can be sprayed or poured on. Multiple layers of the wood replacement surface are allowable, but not required unlike other conventional surfaces.

[0032] Many variations of the disclosed embodiment are possible in accordance with the present invention. The embodiments can be used with boat hulls, decks, docks, floors, buildings or any surface exposed to environmental conditions.

[0033] Having described the invention in detail and by reference to preferred embodiments thereof, it will be apparent that modifications and variations are possible without departing from the scope of the present invention defined in the appended claims. Other suitable materials may be substituted for those specifically recited herein.

## Claims

1. A method of repairing a wood surface with a wood replacement surface comprising:

removing a wood surface from a structure to form an open area;  
 spraying or pouring a wood replacement composition and a catalyst onto said open area, to form a wood replacement surface, said wood replacement composition comprising:

a resin selected from the group polyester resins, vinyl ester resins, and combinations thereof;  
a monomer;  
a thickening agent;  
accelerators; and  
fillers,

wherein the resin, the monomer, the thickening agent, the accelerators, and the fillers are thoroughly mixed together prior to being used as a wood replacement composition.

2. The method of claim 1, wherein the catalyst is methyl ethyl ketone peroxide.
3. The method of claim 1 or 2, wherein the structure is a wood deck.
4. The method of at least one of the preceding claims, wherein the structure is a boat hull.
5. The method of at least one of the preceding claims, wherein the wood replacement surface is able to hold a fastener.
6. The method of at least one of the preceding claims, wherein the wood replacement composition comprises by weight:

10-20%	vinyl ester resin
40-60%	polyester resin
0-20%	monomer
1-15%	thickening agent
0-3%	fumed silica
0.1-5%	accelerators, and
1-25%	fillers.

7. A method of making a sprayable, pourable composition comprising:

providing a vinyl ester resin of 10-20 weight percent of the composition;  
providing a polyester resin of 40-60 weight percent of the composition;  
providing a monomer of 0-20 weight percent of the composition;  
providing 1-15% thickening agent;  
mixing for about 15 minutes;  
providing 0.1-5 weight percent accelerators selected from the group consisting of DMPT, DMA, DMAA cobalt octoate, potassium octoate, copper naphthanate, quaternary ammonium salts and mixtures thereof and 0-3 weight percent fumed silica;  
mixing for about 5 minutes;  
providing filler of 1-25 weight percent of the composition; and  
mixing for about 20 minutes.

8. The method of claim 7 further comprising:

filtering the composition through a mesh filter.

9. A sprayable, pourable composition useful as substitute for wood comprising:

a resin selected from the group consisting of polyester resins, vinyl ester resins, and combinations thereof;  
a monomer;  
a thickening agent;  
accelerators; and  
fillers;

wherein the resin, the monomer, thickening agent; the accelerators, and the fillers are thoroughly mixed together and added to a catalyst prior to being used as a wood substitute.

10. The composition of claim 9, wherein the accelerators comprise at least one material selected from the group consisting of DMPT, DMA, DMAA cobalt octoate, potassium octoate, copper naphthanate, quaternary ammonium salts, and mixtures thereof.

11. The composition of claim 9 or 10, wherein the fillers comprise hollow microspheres and at least one material selected from the group consisting of potassium aluminum silicate and calcium silicate and wherein said thickening agent is thixotropic clays.

12. The composition of claim 11, wherein the hollow microspheres are comprised of a material selected from the group consisting of silicate glass, ceramic and plastic microspheres.

13. The composition of at least one of claims 9 to 12, further including fumed silica.

14. The composition of at least one of claims 9 to 13, wherein the composition comprises by weight:

10-20%	vinyl ester resin;
40-60%	polyester resin;
0-20%	monomer;
1-15%	thickening agent;
0-3%	fumed silica;
0.1-5%	accelerators, and
1-25%	fillers.

15. A boat hull comprising:

at least one fiber reinforced synthetic plastic layer,  
an intermediate layer of a desired thickness formed from mixing resin, a monomer, thickening agent, accelerators, filler, and a catalyst, and  
an outer layer.

16. The boat hull of claim 15, wherein said intermediate layer is formed from a composition comprising by weight:

10-20%	vinyl ester resin;
40-60	polyester resin;
0-20%	monomer;
1-15%	thickening agent;
0-3%	fumed silica;
0.1-5%	accelerators, and
1-25%	filler,

mixed with a catalyst.

17. The boat hull of claim 15 or 16 wherein the filler comprises hollow microspheres and at least one material selected from potassium aluminum silicate and calcium silicate, and wherein said thickening agent is thixotropic clays.

18. The boat hull of claim 17 wherein the hollow microspheres are comprised of a material selected from the group consisting of silicate glass, ceramic and plastic microspheres.

19. The boat hull of at least one of claims 15 to 18 wherein said accelerators comprise at least one material selected from the group consisting of DMPT, DMA, DMAA cobalt octoate, potassium octoate, copper naphthanate, quaternary ammonium salts, and mixtures thereof.

20. The boat hull of at least one of claims 15 to 19, wherein said intermediate layer has a shear strength of about 705 psi, a compressive strength of about 2544 psi, and a water absorption of about 0.2 percent.




FIG. 1




FIG. 2




FIG. 3




FIG. 4